Materials Guide



	% of Recycled Material	Structural Warranty	Finish Warranty	Care and Maintenance	Recommended Disinfectant
Thermory	sustainably sourced	10-year limited	None; naturally weathers to a silver-gray if left untreated	Clean with mild soap and water; let dry. To maintain original color, regularly apply deck oil such as Cutek Extreme Wood Protection Oil	2:1 mix of water and vinegar/add some dish soap. Use brush to scrub surfaces. Rinse and let dry. Wipe down with 3% hydrogen peroxide which will foam and disinfect
Recycled Plastic	95% with 90% coming from post-consumer content	20-year limited that also covers splitting, fungal decay and insect damage		Clean with mild soap and water	Wipe with disinfecting wipes or 70% isopropyl Alcohol
Fusion Advantage TM	steel contains an average of 70%	7-year against rusting, peeling, chip or cracking, mold, mildew, fading and defects in materials and/or workmanship		Clean with mild soap and water	Wipe with disinfecting wipes or 70% isopropyl Alcohol. Please Note: Chlorine Bleach may cause surface discoloration
Powder Coat Steel	average of 70%	3-year against rusting,peeling, chip or cracking, mold, mildew, and defects in materials and/or workmanship; 7-year against fading		Clean with mild soap and water	Wipe with disinfecting wipes or 70% isopropyl Alcohol. Please Note: Chlorine Bleach may cause surface discoloration
Polyethylene Plastic	average of 20%	5-year limited	None	Clean with mild soap and water	Wipe with disinfecting wipes or 70% isopropyl Alcohol
Stainless Steel	average of 70%	20-year limited	None	Use non-abrasive cleaner that is formulated for stainless steel	Wipe with 70% isopropyl alcohol. 3%-6% Hydrogen Peroxide may also be used. Please Note: Chlorine Bleach will cause corrosion and surface discoloration
Aluminum Powder Coated Planters	average of 85%	20-year limited	3-year finish against rusting, peeling, chipping cracking, mold and mildew; 7-year against fading	Remove loose surface deposits with wet sponge. Using soft brush, mild detergent and warm water, remove dust and other deposits; rinse thoroughly	Please Note: Chlorine Bleach will cause corrosion and surface discoloration